


## ■ Reflectivity Change after 1 min of Processing

### ● Si capped ML

Correspond to 70~80 nm of carbon film removal.




#### Average

	before	after	diff.*
Processed	63.6 %	64.0 %	+0.4 %
Reference	63.6 %	63.7 %	+0.1 %

\* Measurement errors and secular changes are included.

◆ No degradation was observed.

### ● Ru-alloy capped ML



#### Average

	before	after	diff.*
Processed	63.7 %	61.9 %	-1.8 %
Reference	-	63.4 %	-

\* Measurement errors and secular changes are included.

◆ ~2 % of reflectivity down.